

FTB

FTB MULTI

ART NR 80.251

UNIVERSAL EPOXY-BINDING AGENT WITH A BROAD PALLET OF APPLICATION POSSIBILITIES

DESCRIPTION

FTB MULTI IS A POLYVALENT EPOXY BINDING AGENT, VERY EASY IN USE AND WITH EXCELLENT CHARACTERISTICS. BECAUSE OF ITS UNIVERSAL CHARACTER IT IS USED IN A VERY LARGE NUMBER OF AREAS.

- COMPONENT A: MODIFIED EPOXY RESIN
- COMPONENT B: POLYAMINE HARDENER

APPLICATION

FTB MULTI IS USED FOR FAST AND DURABLE REPAIRS AND RE-PROFILING OF EXISTING FLOORS. THIS PRODUCT IS ALSO SUITABLE AS PRIMER, SHRINK-FREE GLUE-SEAM, INJECTION RESIN, ETC. ITS LIQUID-TIGHT CHARACTER MAKES IT AS AN UTMOST CHEMICAL RESISTANT COATING AND PROTECTION OF THE SUPPORT.

METHOD OF WORKING

BECAUSE OF ITS SELECTED HARDENER, IT IS POSSIBLE TO MAKE JUST AS MUCH PRODUCT AS NEEDED. THE SIMPLE MIXING PROPORTION OF TWO VOLUME-PARTS "RESIN" TO ONE VOLUME-PART "HARDENER", MAKES THE PRODUCT VERY PROFITABLE, NEVER MORE HARDENED GLUE-RESTS TO THROW AWAY. BY SMOOTHING FTB MULTI AFTER MIXING WITH A PAINT-ROLLER IS OBTAINED A VERY STRONG WEAR-LAYER. WHEN IN THE STILL WET COATING DRY QUARTZ GRANULATES ARE SCATTERED, A ANTI-SLIP FLOOR IS OBTAINED, WHICH IS PRACTICABLE THE DAY AFTERWARDS. THE ANTI-SLIP DEGREE DEPENDS ON THE QUANTITY AND THE SIZE OF THE GRANULATES. CHEMICAL ANCHORS IN CONCRETE OR ANOTHER SUPPORT CAN BE EXECUTED WITHOUT PROBLEMS, BY POURING PARTIALLY THE DRILLING HOLE WITH FTB MULTI, AND IMMEDIATELY THEREAFTER PUTTING THE ANCHOR AND/OR THE THREADED BAR IN THE HOLE. HORIZONTAL ANCHORS CAN BE EXECUTED BY ADDING FTB TIXO TO FTB MULTI, BECAUSE OF THIS A JELLY CONSISTENCY IS OBTAINED, WHICH IS NOT FLOWING AWAY.

THE OPTIMUM TEMPERATURE FOR TREATMENT IS 16°C. LOWER TEMPERATURES GIVE A LONGER HARDENING TIME. THE SURFACE TEMPERATURE OF THE SUPPORT AND THE TEMPERATURE OF THE MATERIALS MUST ALWAYS BE MORE THAN 5°C.

ATTENTION: ALWAYS USE FTB MULTI IN THE PROPORTION 2/1 !. USING MORE OR LESS HARDENER RESULTS IN A NOT OR BADLY HARDENED PRODUCT.

■ **CLEANING OF THE MATERIAL**

WITH FTB CLEAN 1.

■ **CONDITIONING**

1,5 KG AND 7,5 KG

■ **STORAGE TIME**

MAXIMUM 1 YEAR IN ORIGINAL CLOSED CONDITIONING, FROST-FREE AND UNDER ROOF.

■ **PRECAUTIONS**

AVOID CONTACT WITH THE SKIN. WASH HANDS WITH WATER AND SOAP BEFORE EATING.
ENSURE A GOOD VENTILATION OF THE AREA DURING THE PREPARATION AND THE APPLICATION OF THE PRODUCT.

■ **EPILOGUE**

OUR TECHNICAL INFORMATION IS BASED ON OUR OWN EXPERIENCE AND IS GIVEN IN GOOD FAITH. WE GUARANTEE A CONSTANT QUALITY OF OUR PRODUCTS, BUT WE CANNOT ACCEPT ANY RESPONSIBILITY CONCERNING THEIR APPLICATION.