

FTB

FTB DECAP-ALL 2K

ART NR 90.203

PAINT STRIPPER FOR ALMOST ALL 2 COMPONENT PAINTS, THAT ARE RESISTANT AGAINST SOLVENTS

DESCRIPTION

FTB DECAP-ALL 2K IS AN ENVIRONMENT FRIENDLY MIXTURE OF VERY POWERFUL AND DEEP PENETRATING SOLVENTS. IT REMOVES NEARLY ALL 2 COMPONENTS PAINTS, EPOXY AND DD-PAINT, ACRYL, SYNTHETIC RESIN PAINT, LASURE PAINT, NITROCELLULOSE, RESTS OF ADHESIVES AND PU-FOAM ON ALL SURFACES RESISTANT AGAINST SOLVENTS (METAL, WOOD, STONE, ETC.).

METHOD OF WORKING

PROCEDURES: SPRAY (AIRLESS OR AIR-MIX), SMEAR, ROLL.

IF POSSIBLE APPLY FTB DECAP-ALL 2K WITH A N AIR PRESSURE APPARATUS ON THE DESIRED SURFACES. IN CASE OF SEVERAL PAINT LAYERS THIS PROCEDURE HAS TO BE REPEATED EVENTUALLY AFTER THE REMOVAL OF THE DISSOLVED LAYERS. THE APPLICATION WITH BRUSH OR ROLLER IS ONLY FOR SMALL SURFACES AND DIFFICULT TO REACH PLACES.

TEMPERATURE LIMITS FOR THE TREATMENT: + 10°C - + 30°C

TREAT SURFACES AFTERWARDS WITH A SCRAPER, A RUBBER WIPER OR A HIGH PRESSURE CLEANER.

CHARACTERISTICS

ORANGE-RED JELLY LIQUID.

DENSITY: 1,01 g/cm³

PH-VALUE: 2 – 3

ACTION TIME: 0,5 - 24 HOURS.

CONSUMPTION

0,3 TO 1 LITRES/M²

CONDITIONING

25 LTR

■ **STORAGE TIME**

1 YEAR IN CLOSED CONDITIONING AND FROST-FREE.

■ **PRECAUTIONS**

EVENTUALLY COVER THE SURFACES THAT NOT HAVE TO BE TREATED AVOID UNDESIRE CONTACT WITH METALS.

DO NOT COLLECT THE REMOVED PAINT RESTS AND THE CLEANING WATER IN METAL DRUMS.

■ **EPILOGUE**

OUR TECHNICAL INFORMATION IS BASED ON OUR OWN EXPERIENCE AND IS GIVEN IN GOOD FAITH. WE GUARANTEE A CONSTANT QUALITY OF OUR PRODUCTS, BUT WE CANNOT ACCEPT ANY RESPONSIBILITY CONCERNING THEIR APPLICATION.