

FTB

FTB DECAP-ALL RED

ART NR 90.208

PAINT STRIPPER FOR IN- AND OUTSIDE USE. SPECIAL FORMULA FOR REMOVAL OF PAINT ON LEAD BASIS, LIME PAINTING AND OLD PAINT LAYERS IN ONE SINGLE APPLICATION

DESCRIPTION

FTB DECAP-ALL RED IS A PAINT STRIPPER FOR IN- AND OUTSIDE USE.

COMPOSITION

FTB DECAP-ALL RED IS AN ALKALI PASTE ON WATER BASE, WITH A HIGH VISCOSITY. THE PRODUCT IS BIODEGRADABLE AND IT HAS A HIGH COVERING CAPACITY AND A HIGH ADHESIVE CAPACITY.

APPLICATION

FTB DECAP-ALL RED IS SPECIALLY FORMULATED FOR THE REMOVAL OF PAINT ON LEAD BASIS AND/OR OTHER FINISHING COATS AND REMOVES SEVERAL LAYERS OF OLD PAINT IN ONE SINGLE APPLICATION. THE PRODUCT CAN BE APPLIED WITH A TROWEL OR IN THE FORM OF A SPRAY AND ADHERES TO ANY SURFACE, VERTICAL, HORIZONTAL OR ABOVE THE HEAD. BECAUSE OF ITS SELF-FILLING CHARACTERISTICS IT IS POSSIBLE TO WORK CONTINUOUSLY IN A WET ENVIRONMENT WITHOUT NEEDING ANY PROTECTIVE COVERING.

METHOD OF WORKING

TEST-STRIPS:

AS WHEN STRIPPING PAINT MOSTLY DIFFERENT PAINT TYPES AND THICKNESS ARE PRESENT, IT IS NECESSARY TO DO A TEST ON A LIMITED SURFACE IN ORDER TO DETERMINATE THE EFFICIENCY AND THE SUITABLE THICKNESS OF FTB DECAP-ALL RED TO REMOVE THE EXISTING OLD PAINT LAYERS. IT SHOULD ALSO BE CHECKED IF THERE ARE NO HARMFUL EFFECTS ON THE SURFACE THROUGH THE TREATMENT WITH FTB DECAP-ALL RED. A TEST-STRIP WITH A THICKNESS OF APPROX. 2 MM IS APPLIED. IT IS COVERED WITH FTB DECAP-ALL RED PAPER DURING 24 HOURS. THE EFFICIENCY IS EVALUATED AFTER THE REMOVAL OF THE PAPER.

PREPARATION:

CHECK IF THE SURFACE IS ALKALI-RESISTANT. PROTECT THE AREAS THAT DON'T NEED TO BE STRIPPED WITH POLYETHYLENE AND MASKING TAPE.

NOTE: FTB Decap-All Red will not attack glass or plastic surfaces, but it will etch aluminium. Some wood species can also become darker when they come in touch with a strong alkali product.

IF THE TEST STRIPS DON'T GIVE THE DESIRED RESULTS: UNDER NO CIRCUMSTANCES CONTINUE WITH FTB Decap-All Red, but take contact with the manufacturer.

TREATMENT:

APPLY A 3 TO 6 MM LAYER OF PASTE, DEPENDING ON THE AGE AND THE THICKNESS OF THE PAINT, WITH A TROWEL OR A SPRAY-GUN. IRREGULAR SURFACES CAN BE SMEARED BEST WITH A SYNTHETIC BRUSH AS FTB Decap-All Red can also be applied sufficiently thick in the grooves, slits and cracks. AFTER APPLYING THE PASTE PUTT THE SPECIAL FTB Decap-All Red PAPER WITH THE TEXT OUTSIDE. IT ENABLES TO REMOVE VERY EASILY THE PAINT. PAY ATTENTION THAT NO AIR IS CAUGHT UNDER THE PAPER. LET THE PASTE 24 HOURS OR LONGER, DEPENDING ON THE RESULTS OF THE TEST STRIPS. REMOVE THE PAINT BY TURNING WITH A KNIFE IN THE DRIED PASTE AROUND THE SEAMS AND TAKE THE PAINT WITH THE PASTE TOGETHER WITH THE SPECIAL FTB Decap-All Red PAPER IN ONE TIME AWAY. AFTER THE REMOVAL OF THE PAPER WITH FTB Decap-All Red THE "NEUTRALIZER" IS APPLIED WITH A BRUSH (WEAR GLOVES, PH >9). LET SECURE VERY WELL. THE SECURING PROCESS CAN TAKE SEVERAL HOURS, DEPENDING ON THE POROSITY OF THE SURFACE AND THE QUANTITY OF ALKALI ABSORBED. THE AMBIENT TEMPERATURE AND THE RELATIVE HUMIDITY HAVE ALSO AN INFLUENCE ON THE SECURING PROCESS. THE SURFACES MUST BE THOROUGHLY RINSED OUT TO ELIMINATE ALL THE PAINT RESTS AND THE ALKALI RESIDUES. IN CASE OF A TREATMENT OF MASONRY OR NATURAL STONE, THE "NEUTRALIZER" HAS TO BE DILUTED WITH WATER (1/1). FOR PLASTER WORK A DILUTION OF 4 TO 1 WITH WATER IS RECOMMENDED.

REMARK:

THE EFFECTIVENESS OF THE PRODUCT DIMINISHES WHEN IT IS USED AT AN AMBIENT TEMPERATURE LOWER THAN 5°C. THE IDEAL AMBIENT CONDITIONS ARE HIGHER THAN 10°C. AS FTB Decap-All Red IS AN ALKALI PRODUCT, IT WILL NOT WORK ON EPOXY-RESINS, URETHANES, CHLORINATED RUBBER, OR OTHER CHEMICAL TOP COATS.

**CLEANING**

WHEN WORKING OUTSIDE, THE RINSING OF THE RESTS CAN BE ACCELERATED WHEN USING A JET OF WATER. THE CLEANING INSIDE CAN BE DONE WITH A PLANT SPRAY FILLED WITH WATER OR WITH A BUCKET AND A SPONGE. LET DRY DURING 24 HOURS BEFORE STARTING THE NEUTRALIZING PROCESS FOR SURFACES AS WELL INSIDE AS OUTSIDE.

CHARACTERISTICS

FORM:	PASTE
VISCOSITY:	26,5
DENSITY:	1,44
WEIGHT PRO LITRE:	1,2 KG
PERCENTAGE OF VOLATILE SUBSTANCES:	0
PH:	13,0

CONSUMPTION

THE CONSUMPTION OF FTB DECAP-ALL RED DEPENDS ON THE STRUCTURE OF THE SURFACE TO BE TREATED. ON A FLAT WALL WHEN APPLYING 1 MM MATERIAL 15 KG FTB DECAP-ALL RED WILL BE SUFFICIENT TO TREAT APPROX. 11 M². ON THE OTHER HAND WHEN THE SURFACE IS VERY UNEVEN AND 2 MM OF MATERIAL IS APPLIED, THE SAME PACKAGING WILL ONLY BE SUFFICIENT FOR 6 M².

CONDITIONING

16 KG

STORAGE TIME

1 YEAR IN CLOSED CONDITIONING AND FROST-FREE. KEEP AWAY FROM DIRECT SOURCES OF HEAT.

PRECAUTIONS

AVOID CONTACT WITH THE SKIN AND THE EYES. WEAR SUITABLE RUBBER/ PVC GLOVES, PROTECTIVE CLOTHING, SECURITY GLASSES.

WASH STAINS ON THE SKIN IMMEDIATELY WITH WATER AND REMOVE ALL DAMAGED CLOTHING.

EPILOGUE

OUR TECHNICAL INFORMATION IS BASED ON OUR OWN EXPERIENCE AND IS GIVEN IN GOOD FAITH. WE GUARANTEE A CONSTANT QUALITY OF OUR PRODUCTS, BUT WE CANNOT ACCEPT ANY RESPONSIBILITY CONCERNING THEIR APPLICATION.