



FTB REPLICA PROFILE

ART NR 10.963 – 10.961

SPECIAL MORTAR THAT CAN BE PROCESSED WITH THE HANDS AND THAT CAN BE MODELLED

■ DESCRIPTION

FTB REPLICA-PROFILE IS A SPECIAL DEVELOPED MORTAR THAT CAN BE PROCESSED WITH THE HANDS AND THAT CAN BE MODELLED.

■ COMPOSITION

FTB REPLICA-PROFILE IS MADE ON A PORTLAND-CEMENT BASE.

■ APPLICATION

FTB REPLICA-PROFILE IS A MORTAR THAT CAN BE MADE WITH WATER AND THAT HAS A SEMI-PLASTIC CONSISTENCY. IT CAN BE USED FOR INSTANCE TO MAKE REPAIRS, TO “BUILD UP” MODELS, OR WHEN “PULLING” FRAMES MANUALLY.

■ METHOD OF WORKING

MAKE FTB REPLICA-PROFILE ONLY WITH CLEAR WATER. NORMALLY THE RATIO WILL BE 3,5 PARTS PF POWDER TO 1 PART OF WATER (DEPENDING ON THE WANTED CONSISTENCY). THEN MIX THE MORTAR VERY WELL MECHANICALLY. LET THE MORTAR RIPE DURING SOME MINUTES AND MIX AGAIN VERY WELL. DON'T ADD WATER ANYMORE. APPLY THE MORTAR WITH A HAWK. THE MORTAR CAN BE TREATED DURING APPROX. 20 MINUTES (DEPENDING ON THE TEMPERATURE).

CHARACTERISTICS

- FAST BINDING.
- QUICK DEVELOPMENT OF STRENGTH
- EXCEPTIONAL POSITION ABILITY
- RESISTANT AGAINST HUMIDITY
- WEIGHT LOWER THAN TRADITIONAL MORTAR
- CHEAP AND ENVIRONMENT FRIENDLY ALTERNATIVE FOR SYNTHETIC MATERIAL
- NON-FLAMMABLE
- FIXED AND CERTAIN COLOUR
- POSSIBILITY TO ADD DIFFERENT DYES
- SUITABLE FOR IN- AND OUTSIDE USE

CLEANING OF THE MATERIAL

WITH WATER.

CONDITIONING

FTB REPLICA-PROFILE:

- | | |
|---------------------------------|-------|
| - UNCOLOURED (ART. NR. 10.963): | 25 KG |
| - COLOURED (ART. NR. 10.961): | 20 KG |

STORAGE TIME

MINIMUM 6 MONTHS IN CLOSED CONDITIONING. KEPT DRY AND FROST-FREE.

EPILOGUE

OUR TECHNICAL INFORMATION IS BASED ON OUR OWN EXPERIENCE AND IS GIVEN IN GOOD FAITH. WE GUARANTEE A CONSTANT QUALITY OF OUR PRODUCTS, BUT WE CANNOT ACCEPT ANY RESPONSIBILITY CONCERNING THEIR APPLICATION.