



# FTB PRIMER

ART NR 60.100

EPOXY PRIMER FOR HORIZONTAL APPLICATIONS

## DESCRIPTION

---

FTB PRIMER IS A PURE 2-COMPONENT EPOXY-PRIMER, WITHOUT SOLVENTS.

COMPONENT A: EPOXY RESIN OF THE A/F TYPE

COMPONENT B: MODIFIED POLYAMIDE -EPOXY HARDENER

## APPLICATION

---

FTB PRIMER IS USED AS PRIMER OR ADHERENCE LAYER FOR:

- FTB SL
- FTB EM
- FTB EPOCOAT

## METHOD OF WORKING

---

### PREPARATION OF THE SUPPORT:

THE SUPPORT MUST BE CLEAN, DRY, DUST- AND FAT-FREE, STRONG AND WELL COHERENT.  
CEMENT SKIN AND FAT RESTS MUST BE REMOVED. THE SUPPORT MUST BE FREE OF DAMP TENSION.  
CAVITIES IN THE FLOOR MUST BE FILLED.

### TREATMENT:

FTB PRIMER IS MADE BY MIXING INTENSIVELY TO A HOMOGENEOUS MIXTURE THE COMPONENTS A AND B PREPARED IN THE CORRECT DOSAGE.

FTB PRIMER IS APPLIED WITH A BRUSH, A ROLLER OR A RUBBER.

### REMARK:

THE OPTIMAL AMBIENT TEMPERATURE IS 16°C. A LOWER TEMPERATURE WILL HAVE A LONGER HARDENING TIME AS CONSEQUENCE. THE AMBIENT TEMPERATURE MUST ALWAYS BE ABOVE 10°C.

## ■ **CLEANING OF THE MATERIAL**

---

WITH FTB CLEAN 1.

## ■ **CHARACTERISTICS**

---

COLOUR:	YELLOW
POT-LIFE AT 20°C:	30 MINUTES
FLEXURAL STRENGTH:	APPROX. 20 N/MM <sup>2</sup>
DRYING OUT TIME:	± 8 HOURS

## ■ **CONSUMPTION**

---

CA. 0,25 KG/M<sup>2</sup>

## ■ **CONDITIONING**

---

7 KG

## ■ **STORAGE TIME**

---

1 YEAR IN CLOSED CONDITIONING AND FROST-FREE.

## ■ **PRECAUTIONS**

---

AVOID CONTACT TO SKIN. WASH HANDS WITH SOAPY WATER BEFORE EATING OR SMOKING.  
ENSURE A GOOD VENTILATION OF THE AREA DURING THE PREPARATION AND THE APPLICATION OF THE PRODUCT.

## ■ **EPILOGUE**

---

OUR TECHNICAL INFORMATION IS BASED ON OUR OWN EXPERIENCE AND IS GIVEN IN GOOD FAITH. WE GUARANTEE A CONSTANT QUALITY OF OUR PRODUCTS, BUT WE CANNOT ACCEPT ANY RESPONSIBILITY CONCERNING THEIR APPLICATION.